

M/38102-US

H4

98-016949/02

A9-2 F04 (A17 A21 A23)

TOMI- 96.08.05

SC TOMIRIS SA

\*RO 112038-B1

96.08.05 96RO-001590 (97.04.30) D04H 1/04

Nonwoven textile material and mfr. - comprises mixt. of polyester-, polypropylene-, poly-amide-, and melamine- fibres.

C98-006248

Addnl. Data: HUTANU P, MICLIUC V, ARADOAIE V, HEREA D, SAVA C

A(4-G3C, 5-B1, 5-F1C, 11-C5A, 12-C3, 12-R6, 12-S5G) F(2-C1, 2-C2B1, 4-C, 4-E6, 4-F1, 4-F3)

8

Non-woven textile material consist of: 20-60% polyester fibres (60-120mm length and 4-9 denier density of length, 10-40% polypropylene fibres (50-120mm length and 4-15 denier density of length), 10-30% polyamides fibre (55-85mm length and 4-7 denier density of length), 5-40% melamine fibre (60-100mm length and 4-12 denier density of length), chemically consolidated by spraying successively on both sides with 6-35 g/m<sup>2</sup> polyacrylate type adhesives, drying progressively at 70-100°C and 1,2-3.0m/min. in dryer.

USE

Non-woven material used for padding in textile industry or as consolidator, thermal insulator in construction industry.

(1pp2452DwgNo.0/0)

RO 112038-B

\* d